



# ConinsPune



GLOBAL QUALITY THROUGH  
INDIGENOUS TECHNOLOGY




ISO 9001-2008 • C-DOT Approve • Mil-Standard Mil-I-46058C Type AR • RoHs Compliances

## ACRYLCOAT LACQUER

### HOW TO APPLY BY EXTERNAL DISPENSING PUMP & SPRAY GUN

- \* When the production of PCB Assembly. is in quantity the external pump with spray gun & compressed air is used. This is having 1 no air tight cylinder where 5 Liters of ACRYLCOAT is placed connected with a tube and valve.
- \* Then mixing of compressed air and Acrylcoat lacquer in proper combination and air pressure and adjusting the spray nozzle we can spray Acrylcoat to quantity of PCB Assembly. at a time.
- \* Place the PCB Assembly. On the table with coating surface upside in a line close to each other , Adjust the Spray through and air pressure as require. hold the spray gun in the angle required and start spraying uniformly and steadily.
- \* The coating will get spread on surface when it is in liquid stage.
- \* Only ALQ -30 ,ALQ 60 & ALQ-100 can be spray by this method
- \* Once the spraying is over and going to stop for a day, Cleaning of container by ELCLEAN with the tube & spray gun to be done.
- \* Let the all boards get touch to dry then only lift it and start further process.
- \* For faster drying preheating and post heating procedure can adopted.
- \* Continuity test after coating to be done only after 4-6 Hrs
- \* Avoid flames and sparks nearby process.



How to make fast coating for bulk quantity PCB assembly.

#### Pre Heat & Post Heat procedure

- \* For bulk production the drying time required to be shorten / less
- \* Then procedure to be followed as below
- \* Pre heat the tested ok PCB assembly for 1 min. @ 50deg C
- \* Immediately apply the coating
- \* Post heating Again heat the coated PCB for 1-2 min. for faster drying (touch to dry) If required for faster drying.
- \* Proceed for further assembly. (test after 2 hrs of coating )

For preheat & posts heating drying process use of Hot Air blower or Oven or 100 watt bulb cavity can be arrange but it should be open type to vapor the solvents in AIR